



INSULATION JUST GOT BETTER

ArmaGel HTL

Flexible aerogel blanket for high-temperature applications

- // ASTM C1728 Compliant
- // Non-combustible in accordance with ISO EN 1182 (A1)
- // Excellent protection against corrosion under insulation (CUI)
- // Hydrophobic and breathable
- // More choice: 5, 10 and 20 mm thicknesses



 **armacell**[®]
ArmaGel[®]

TECHNICAL DATA - ARMAGEL HTL

Brief description	ArmaGel HTL is a flexible aerogel insulation blanket suitable for high-temperature insulation applications up to 650°C (1200°F). ArmaGel HTL is compliant with ASTM C1728, Type V, Grade 1A.
Material type	Aerogel blanket.
Product colour range	Light grey
Special features	ArmaGel HTL is a highly flexible aerogel insulation blanket. It is hydrophobic and breathable providing the best-in-class corrosion under insulation (CUI) protection.
Product range	Sheets in rolls, 5, 10 and 20 mm (0.2, 0.4 and 0.8 in) thickness and width of 1.5 m (59 in). For further details, please refer to the product range tables at the end of this document.
Applications	Thermal insulation/protection of pipes, vessels, equipment, fittings and etc. in industrial and process facilities.
Installation	For industrial applications it is recommended to consult the relevant Armacell application manual(s). For further information please contact our Technical Services.

Property	Value / Assessment				Standard / Test method	
Temperature range						
Service temperature ¹	Max. °C	Max. °F			ASTM C447, ASTM C411	
	650	1,200				
Thermal conductivity						
Declared thermal conductivity	θm	24°C (75°F)	100°C (212°F)	200°C (392°F)	300°C (572°F)	ASTM C177
	λd ≤ [W/(m·K)]	0.029	0.039	0.049	0.061	
	k ≤ [Btu-in/(h-ft ² -°F)]	0.20	0.27	0.34	0.42	
Fire Performance and Approvals						
Reaction to fire	A1 Non-combustible				ISO 1182, EN 13501-1	
Surface burning characteristics	Flame spread index ≤ 5 Smoke developed index ≤ 10				ASTM E84	
Fire performance						
Toxicity	Passed				KS F 2271	
Resistance to water						
Hydrophobic	Yes					
Water absorption	≤ 8% by weight				ASTM C1763	
Corrosion mitigation						
Stress corrosion cracking	Passed				ASTM C692	
Physical attributes						
Nominal density	150 kg/m ³ (9.5 lb/ft ³)				ASTM C303, KS L 9102	
Weather and UV resistance						
Weather resistance	In all industrial applications the outer layer of the material must be protected with an adequate covering like metal jacketing or preformed UV-cured GRP (Glass-Reinforced Plastic) cladding. Please contact Technical Services for guidance on the temperature limitations and specific construction considerations which need to be made for each jacketing system.					
Health and environment						
Fungal growth	No growth / Rating 0				ASTM C1338, ASTM G21	
Health aspects	Neutral					
Other technical features						
Shelf life ²	Max. 3 years					

Property	Value / Assessment	Standard / Test method
Storage	Material shall be stored indoors, in clean and dry conditions, away from direct sunlight.	

¹For use in temperatures beyond the published value, please contact Technical Services.

²Shelf life (maximum storage time) is limited to ensure that only currently manufactured products are installed on projects. This limitation is restricted solely to storage of the product and does not affect the lifetime of product after it has been installed.

All data and technical information are based on results achieved under the specific conditions defined according to the testing standards referenced. Despite taking every precaution to ensure that said data and technical information are up to date, Armacell does not make any representation or warranty, express or implied, as to the accuracy, content or completeness of said data and technical information. Armacell also does not assume any liability towards any person resulting from the use of said data or technical information. Armacell reserves the right to revoke, modify or amend this document at any moment. It is the customer's responsibility to verify if the product is suitable for the intended application. The responsibility for professional and correct installation and compliance with relevant building regulations lies with the customer. This document does not constitute nor is part of a legal offer to sell or to contract.

At Armacell, your trust means everything to us, so we want to let you know your rights and make it easier for you to understand what information we collect and why we collect it. If you would like to find out about our processing of your data, please visit our Data Protection Policy.

Trademarks followed by © or ™ are trademarks of the Armacell Group. © Armacell, 2024. All rights reserved.

TDS | 032024 | en-GB

ABOUT ARMACELL

As the inventor of flexible foam for equipment insulation and a leading provider of engineered foams, Armacell develops innovative and safe thermal and mechanical solutions that create sustainable value for its customers. Armacell's products significantly contribute to global energy efficiency making a difference around the world every day. With more than 3,300 employees and 25 production plants in 19 countries, the company operates two main businesses, Advanced Insulation and Engineered Foams. Armacell focuses on insulation materials for technical equipment, high-performance foams for acoustic and lightweight applications, recycled PET products, next-generation aerogel technology and passive fire protection systems.



For more information, please visit:
www.armacell.com